

PLA @df

PLA @df is a tough, easy to use high grade PLA type of filament, ideal for 3D printing. Slightly modified, the filament retains the typical features of PLA, but makes it tougher and less brittle. Due to a low shrinkage factor PLA @df will not deform after cooling. Poly Lactic Acid is a biodegradable plastic made from renewable natural resources and one of the most popular materials for 3D printing.

Features:

- Tougher and less brittle compared to regular PLA
- Easy to print at low temperature
- Low warping
- Biodegradable
- Limited smell



Dimensions

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Physical properties

Description	Testmethod	Typical value
Specific gravity	ASTM D1505	1,24 g/cc
MFI	-	6,0 g/10 min
Tensile strength		110 MPa (MD) 145 MPa (TD)
Elongation at break		160% (MD) 100% (TD)
Tensile modulus		3310 MPa (MD) 3860 Mpa (TD)
Impact Strength	-	7,5 KJ/m²

Colours:

PLA @df is available from stock in a large selection of bright colours of which you see a selection beneath. For non stock colours a minimum of 40kg \pm 10% is required.

Thermal properties

Description	Testmethod	Typical value
printing temp.	-	180-210°C
melting temp.	-	210°C ± 10°C
melting point	ASTM D3418	145-160°C
vicat softening temp.	ISO 306	± 60°C

(na) btl (wh) bu) rdl (grl (yl) (orl (si) (pi) (ma) (pw) (yg) (go) (gy) (pu) (brl (bu2 (gr2 (wh2 (ylf (orf (grf (clf (grg

Packaging:

PLA @df is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Additional info:

Due to its low tendency to warp PLA @df can also be printed without a heated bed. If you have a heated bed the recommended temperature is \pm 35-60°C.

PLA @df can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly..

2014-05-26

www.dutchfilaments.com info@dutchfilaments.com

Zuiddijk 13 5705 CS Helmond The Netherlands T: +31 492 549 874